

## TECHNICAL SPECIFICATIONS

### 2 PANELS ARCHTOP RAISED TEXTURED

### B8100/B8120

#### SOLID PARTICLEBOARD CORE DOORS

For regular usage (indoor only)



Mill Option (MO)

Specifications	Description
<b>Size :</b>	Maximum: 914 mm x 2032 mm (36" x 80")
<b>Thickness :</b>	35 mm (1-3/8"), 44 mm (1-3/4")
<b>Stiles :</b>	Door 1 3/8" = 29 mm (1 1/8") of low density wood finger jointed clear pine (MO) Door 1 3/4" = 38 mm (1 1/2") of low density wood finger jointed clear pine (MO)
<b>Rails :</b>	Door 1 3/8" = 29 mm (1 1/8") of low density wood finger jointed knotty or clear pine Door 1 3/4" = 38 mm (1 1/2") of low density wood finger jointed knotty or clear pine
<b>Core :</b>	Particleboard, medium density of 28-32 pounds per foot cube. Conforms to the standard CSA-0188 and standard ANSI A208-1. (LD-1/LD-2). Available NAUF.
<b>Faces :</b>	2 panels archedtop raised textured. Available NAUF.
<b>Adhesive :</b>	Type 1, fully weatherproof; PVA polyvinyl acetate (NAUF); VOC < 14.98 g/L.
<b>Options :</b>	Specify 2 panels archedtop raised textured B8120 [door 44 mm (1-3/4")] Fire rated 20 minutes, neutral pressure (NP) or positive (PP) Contact us for more details on fire rated restrictions (opening, machining, etc...) Bifolds, sliding, swivel, retractable (pocket doors) doors. Prehung doors Doors with low VOC primer Machining on request. Consult our machining charter Stiles and rails with primer or sealed Individual identification (tag) Delivery by floor
<b>Finish :</b>	Primed only or painted in the factory. The top and bottom are sealed. Custom color development.
<b>Programs :</b>	Boccam attests that these models of particleboard core doors contribute to industry programs such as LEED ® , Green Globes and others, contact us!
<b>Standard :</b>	ANSI/WDMA I.S. 1 A-2013 ; CAN/CSA 0132.2 Series-90(R1998) AWI/AWMAC WI 2nd Edition, 01 October, 2014
<b>Warranty :</b>	Covered by a limited warranty of 1 year against manufacturing defects. Please contact us for more details.

Note : The stiles and rails dimensions are untrimmed. These dimensions will vary according to the fit of the finished dimensions.

For more information, consult the Technical Data Chart.